

PRODUCT SPECIFICATION

HandPRO.

NITRILE EXAM GLOVES

240mm (9") Length

100% Nitrile

Powder-Free

Non-Sterile

Finger-Textured Surface

Chemotherapy Drug Permeation Tested

Blue Color

Ambidextrous

Beaded Cuff





EN 455





QUALITY & CONFORMITY

- Manufactured under ISO 13485, ISO 9001, and US FDA QSR Quality Management System
- Conforms to ASTM D6319 and EN455
- EU Certificate 0321.10015-01.E00-00 (Type B, CE 0321)
- Complies with FDA CFR 21 177.2600 and European Commission Regulation (EU) No. 10/2011 for food handling
- · Conforms to the following additional test standards:

ASTM D412 Tensile Properties of Vulcanized Rubbers

ASTM D3578 Standard Specification for Rubber Examination Gloves
ASTM D5151-99 Standard Test for Detection of Holes in Medical Gloves
ASTM D573 Accelerated Aging for Rubber (at 70° C for 166hr)
Test Method for Residual Powder on Medical Gloves

ASTM D6978 Chemotherapy Drug Permeation Test

ASTM F1671-13 Viral Penetration Test

PERFORMANCE REQUIREMENTS

Characteristic	Inspection Level	AQL	
Freedom from Holes	G1	1.5	
Visual Defects (Major)	G1	2.5	
Visual Defects (Minor)	G1	4.0	
Physical Properties	S2	4.0	
Physical Dimensions	S2	4.0	
Powder Residue	-	2mg/glove (Max)	

ESD PROPERTIES

HandPRO® AirSoft900™ is a Static Dissipative Nitrile Exam Glove

PRODUCT NUMBERS

Size	Item#	Case Quantity	
X-Small	900	1000	
Small	901	1000	
Medium	902	1000	
Large	903	1000	
X-Large*	904	1000	

PHYSICAL DIMENSIONS

Size	X-Small (5/6)	Small (6/7)	Medium (7/8)	Large (8/9)	X-Large (9/10)
Palm Width ± 5 mm	75	85	95	106	116
Glove Length (mm)	Typical Value 242 - 248 (240 Minimum)				
Thickness (mm) Cuff (25 ± 5 mm from bead) Palm (center of palm) Finger (13 ± 3 mm from tip)	Typical Value 0.05 - 0.06 (0.05 Minimum) Typical Value 0.07 - 0.08 (0.06 Minimum) Typical Value 0.12 - 0.14 (0.08 Minimum)				

PACKAGING

100 gloves per box, 10 boxes per case.

SHELF LIFE & STORAGE

Five years from date of manufacture. Store in a cool, dry place away from direct sunlight.

PHYSICAL PROPERTIES

Test	Before	Aging	After Aging		
	Minimum	Typical Value	Minimum	Typical Value	
Tensile Strength (MPa)	14	26.79-39.61	14	24.95-43.29	
Ultimate Elongation	500%	580-656%	400%	504-588%	

Manufactured in Malaysia for Hourglass International, Inc.

The information on this document is a guideline of typical values and characteristics of the product.

The specifications provided reflect the minimum acceptable requirements of the ASTM and FDA where applicable. Actual testing results are available upon request. Gloves offered by Hourglass International, Inc. meet or exceed these physical requirements. Independent laboratory test results are available upon request.

Your Protection Is Our Purpose





(800) 277-0994



