Amplitude[™] Epsilon[™]

Nonwoven cellulose/polyester hydroentangled wipe

Description

Made of 55% special grade blue cellulose and 45% polyester hydroentangled to form a wipe with improved cleanliness and excellent sorbency. The cellulose uses a dye-fast color, to minimize color bleeding. The blue color allows for differentiation between wipes used in different areas. These wipes are strong and durable and contain low levels of particles and extractables. Good for wet areas requiring spill pickup and cleanup.

Technical Data

Wipe material

Wipe construction	Hydroentangled		
Attribute; (units)	Value	Test Method	
Basis weight; nominal (g/m²)	71	Contec Method	
Sorbency in water			
Intrinsic; (mL/g)	4.3	IEST-RP-CC004.3, Sec. 8.1	
Extrinsic; (mL/m²)	291	IEST-RP-CC004.3, Sec. 8.1	
Sorptive rate; (seconds)	<1.0		
Non-volatile residue, NVR		IEST-RP-CC004.3, Sec. 7.1.2	
In deionized water; (g/m²)	0.017		
In isopropanol; (g/m²)	0.023		
Specific ions		IEST-RP-CC004.3, Sec. 7.2.2	
Sodium; (ppm)	39.2		

10.4

25.2

25

Chloride; (ppm)

 $P \ge 0.5 \mu m$; $(x10^6/m^2)$

Particles, readily releasable

Fibers > $100 \mu m$; (x10³/m²)

Cellulose/polyester

Part Number	Description	EA/OB1	OB1/OB2	OB2/CS	EA/CS
AMEP0001	Amplitude Epsilon Wipes, 9" x 9" (23 x 23cm), blue	300	1	12	3600
AMEP0002	Amplitude Epsilon Wipes, 12" x 12" (30 x 30cm), blue	150	1	20	3000

Key: EA = Each, OB1 = Outer Bag 1, OB2 = Outer Bag 2, CS = Case

Notes:

- 1) The information presented here is applicable to the part numbers shown above as well as to any product containing the same materials and produced under the same conditions, regardless of product size or packaging configuration. Please contact a Contec sales representative for more details.
- 2) Data shown are typical values and should not be used as product specifications.
- 2) Valid product comparisons may only be obtained through side-by-side testing in the same test facility, under similar conditions.
- 4) Current and/or comparison data may be available. Please contact a Contec sales representative for details.

Revision date: 08/21/15 ETR 2697, 2698, 2699

IEST-RP-CC004.2, Sec. 5.1

IEST-RP-CC004.2, Sec. 5.2



Europe